Plysolene Limited

Unit 21 Star Road Industrial Estate Partridge Green West Sussex RH13 8RA

Tel: 01403 713555

e-mail: sales@plysolene.co.uk website: www.plysolene.co.uk



Agrément Certificate 05/4201

Product Sheet 3 Issue 4

PLYLOAD HIGH PERFORMANCE DAMP-PROOF

COURSES PLYLOAD TRADE

This Agrément Certificate Product Sheet⁽¹⁾relates to Plyload Trade, for use in walls as a horizontal, vertical or stepped damp-proof course (DPC) in either solid or cavity walls of brick, block, stone or concrete.

(1) Hereinafter referred to as 'Certificate'.

The assessment includes

Product factors:

- · compliance with Building Regulations
- compliance with additional regulatory or nonregulatory information where applicable
- · evaluation against technical specifications
- · assessment criteria and technical investigations
- · uses and design considerations

Process factors:

- · compliance with Scheme requirements
- · installation, delivery, handling and storage
- production and quality controls
- · maintenance and repair

Ongoing contractual Scheme elements†:

- regular assessment of production
- formal 3-yearly review



KEY FACTORS ASSESSED

Section 1. Mechanical resistance and stability

Section 2. Safety in case of fire

Section 3. Hygiene, health and the environment

Section 4. Safety and accessibility in use

Section 5. Protection against noise

Section 6. Energy economy and heat retention

Section 7. Sustainable use of natural resources

Section 8. Durability

The BBA has awarded this Certificate to the company named above for the product described herein. This product has been assessed by the BBA as being fit for its intended use provided it is installed, used and maintained as set out in this Certificate.

On behalf of the British Board of Agrément Date of Fourth issue: 20 September 2023 Originally certificated on 14 February 2005

Hardy Giesler

Chief Executive Officer

This BBA Agrément Certificate is issued under the BBA's Inspection Body accreditation to ISO/IEC 17020. Sections marked with † are not issued under accreditation. The BBA is a UKAS accredited Inspection Body (No. 4345), Certification Body (No. 0113) and Testing Laboratory (No. 0357).

Readers MUST check that this is the latest issue of this Agrément Certificate by either referring to the BBA website or contacting the BBA directly.

The Certificate should be read in full as it may be misleading to read clauses in isolation.

Any photographs are for illustrative purposes only, do not constitute advice and should not be relied upon.

British Board of Agrément

1st Floor Building 3, Hatters

Lane Croxley Park, Watford

Herts WD18 8YG

Equation 1923 665300 clientservices@bbacerts.co.

Equation 1923 665300 clientservices@bbacerts.co.

Equation 1923 665300 clientservices@bbacerts.co.

Equation 1923 665300 clientservices@bbacerts.co.

Plysolene Ltd 21 Star Industrial Estate, Partridge Green, West Sussex, RH13 8RA

Watts
Part of the Watts Group

Page 1 of 11

SUMMARY OF ASSESSMENT AND COMPLIANCE

This section provides a summary of the assessment conclusions; readers should refer to the later sections of this Certificate for information about the assessments carried out.

Compliance with Regulations

Having assessed the key factors, the opinion of the BBA is that Plyload Trade, if installed, used and maintained in accordance with this Certificate, can satisfy or contribute to satisfying the relevant requirements of the following Building Regulations:



The Building Regulations 2010 (England and Wales) (as amended)

Requirement: A1 Loading

Comment: The product can contribute to satisfying this Requirement. See section 1

of this Certificate.

Requirement: B4(1) External fire spread

Comment: The product is restricted by this Requirement in some cases. See section 2

of this Certificate.

Requirement: C2(a)(b) Resistance to moisture

Comment: The product will enable a wall to satisfy this Requirement. See section 3

of this Certificate.

Regulation: 7(1) Materials and workmanship

Comment: The product is acceptable. See sections 8 and 9 of this Certificate.

The Building (Scotland) Regulations 2004 (as amended)

Regulation: 8(1) Fitness and durability of materials and workmanship

Comment: The use of the product satisfies the requirements of this Regulation. See

sections 8 and 9 of this Certificate.

Regulation: 9 Building standards - construction

Standard: 1.1(a)(b) Structure

Comment: The product can contribute to satisfying the requirements of this Standard,

with reference to clause $1.1.1^{(1)(2)}$. See section 1 of this Certificate.

Standard: 2.6 Spread to neighbouring buildings

Comment: The product is restricted under clauses 2.6.5⁽¹⁾ and 2.6.6⁽²⁾ of this

Standard. See section 2 of this Certificate.

Standard: 3.4 Moisture from the ground

Standard: 3.10 Precipitation

Comment: The product will enable a wall to satisfy the requirements of these Standards, with

reference to clauses $3.4.1^{(1)(2)}$ and $3.10.1^{(1)(2)}$. See section 3 of this Certificate.

Standard: 7.1(a) Statement of sustainability

Comment: The product can contribute to satisfying the relevant requirements of Regulation

9, Standards 1 to 6, and therefore will contribute to a construction meeting a

bronze level of sustainability as defined in this Standard.



Page 2 of 11

Regulation: 12 Building standards - renovations

Comment: All comments given for the product under Regulation 9, Standards 1 to 6, also

apply to this Regulation, with reference to clause $0.12.1^{(1)(2)}$ and Schedule $6^{(1)(2)}$.

(1) Technical Handbook (Domestic).(2) Technical Handbook (Non-Domestic).

The Building Regulations (Northern Ireland) 2012 (as amended)

Regulation: 23(1)(a)(i) Fitness of materials and workmanship

Comment: (iii)(b)(i) The product is acceptable. See sections 8 and 9 of this Certificate.

Regulation: 28(a)(b) Resistance to moisture and weather

Comment: The product will enable a wall to satisfy the requirements of this

Regulation. See section 3 of this Certificate.

Regulation: 30 Stability

Comment: The product can contribute to satisfying the requirements of this

Regulation. See section 1 of this Certificate.

Regulation: 36(a) External fire spread

Comment: The product is restricted by this Regulation in some cases. See section

2 of this Certificate.

Additional

NHBC Standards 2023

In the opinion of the BBA, Plyload Trade, if installed, used and maintained in accordance with this Certificate, can satisfy or contribute to satisfying the relevant requirements in relation to *NHBC Standards*, Chapter 6.1 *External masonry walls*.

Fulfilment of Requirements

The BBA has judged Plyload Trade to be satisfactory for use as described in this Certificate. The product has been assessed for use in walls as a horizontal, vertical or stepped damp-proof course (DPC) in either solid or cavity walls of brick, block, stone or concrete.

ASSESSMENT

Product description and intended use

The Certificate holder provided the following description for the product under assessment. Plyload Trade consists of flexible sheets, manufactured from a blend of thermoplastic polymers and other additives, and extruded into roll form.


The product has the nominal characteristics given in Table 1.

Table 1 Nominal characteristics of Plyloa	d Trade
Characteristic (unit)	Value
Thickness (mm)	0.60
Mass (kg·m ⁻²)	0.58
Roll length (m)	20
Roll width (mm)	100-1000
Colour	Black

Preformed cavity tray units are flexible units for angles in stepper or horizontal damp-proof coursing. Typical examples are shown in Figure 1.



Page 3 of 11



Cavity trays, steps, angles and stop ends are pre-formed in the factory (see Figure 1). These components may be used separately or with each other.

Product assessment - key factors

The product was assessed for the following key factors, and the outcomes of the assessments are shown below. Conclusions relating to the Building Regulations apply to the whole of the UK unless otherwise stated.

1 Mechanical resistance and stability

Data were assessed for the following characteristic.

- 1.1 Behaviour under load
- 1.1.1 Results of behaviour under load tests are given in Table 2.

Table 2 Results of behavio	ur under load tests		
Product assessed	Assessment method	Requirement	Result
Representative related product	Shear resistance to BS DD 86-1 : 1983	Value achieved	0.35 N·mm ⁻²

1.1.2 Plyload Trade will not extrude under load, up to the point of compressive failure of the wall and will not adversely affect the ability of a properly designed and built wall to sustain and transmit compression.

2 Safety in case of fire

Data were assessed for the following characteristic.

- 2.1 Reaction to fire
- 2.1.1 The Certificate holder has not declared a reaction to fire classification for the product to BS EN 13501-1: 2018.
- 2.1.2 On the basis of data assessed, the product will be restricted in use under the documents supporting the national Building Regulations in some cases.
- 2.1.3 In England, the product must not be used in external walls of buildings that have a storey at least 18 m above ground level and contain one or more dwellings, an institution for residential purposes, student accommodation, care homes, sheltered housing, hospitals and dormitories in boarding schools.

Watts

Plysolene Ltd 21 Star Industrial Estate, Partridge Green, West Sussex, RH13 8RA

Page 4 of 11

- 2.1.4 In Northern Ireland, the product must not be used in external walls of buildings that have a storey at least 18 m above ground level and contain one or more dwellings, an institution for residential purposes (excluding any room in a hostel, hotel or boarding house), student accommodation, care homes, sheltered housing, hospitals, dormitories in boarding schools, nursing homes and places of lawful detention.
- 2.1.5 In Scotland, the product must not be used in external walls 1 m or less from a boundary or domestic buildings with a storey at a height of more than 18 m above the ground.

3 Hygiene, health and the environment

Data were assessed for the following characteristics.

- 3.1 Resistance to water and water vapour
- 3.1.1 Results of resistance to water and water vapour tests are given in Table 3.

Table 3 Results of resista	ance to water and water vapour tes	ts	
Product assessed	Assessment method	Requirement	Result
Plyload Trade	Determination of watertightness to BS EN 1928 : 2000 under 2 kPa water pressure for 24 hours	No leakage	Pass
	Determination of water vapour transmission properties to BS EN 1931 : 2000	Value achieved	sd = 73 m

- 3.1.2 When correctly specified and installed, the product will provide an effective barrier against liquid water and water vapour, either from a source external to the structure or from one part of the structure to another.
- 3.2 Resistance to mechanical damage
- 3.2.1 Results of resistance to mechanical damage tests are given in Table 4.

Table 4 Results of resist	ance to mechanical damage test	S	
Product assessed	Assessment method	Requirement	Result
Plyload Trade	Determination of resistance to impact to BS EN 12691 : 2006	No leakage at 250 mm drop height	Pass
	(Method A)		
	Determination of	Value achieved	
	resistance to tearing (nail	Machine direction	269 N
	shank) to BS EN 12310-1 : 2000	Cross direction	261 N
	Determination of shear resistance of joints to BS EN 12317-2 : 2000	Value achieved	153 N·(50mm)⁻¹
	Resistance to static loading to BS EN 12730 : 2001 (Method B)	No leakage	Pass

3.2.2 The product will withstand considerable movement of the wall and is unlikely to be impaired by normally occurring movements up to the point where the wall itself is deemed to have failed.

E sales@plysolene.co.uk

T 01403 713555

4 Safety and accessibility in use

Not applicable.

5 Protection against noise

Not applicable.

6 Energy economy and heat retention

Not applicable.

7 Sustainable use of natural resources

Not applicable.

8 Durability

8.1 The potential mechanisms for degradation and the known performance characteristics of the materials in this product were assessed.

8.2 Specific test data were assessed as given in Table 5.

Product assessed	Assessment method	Requirement	Result
	Determination of watertightness to	No evidence of water penetration after 24 hours	Pass
Plyload	BS EN 1928 : 2000 after	of 2 kPa pressure	
Trade	exposure to alkali		
	Determination of watertightness to BS EN 1928 : 2000 after heat ageing (70oC for 12 weeks)	No evidence of water penetration after 24 hours of 2 kPa pressure	Pass
	Resistance to low temperature to BS EN 495-5 : 2001	No cracks	-40°C

^{8.3} The product is compatible with all normal construction materials with which it is likely to be in contact.

8.4 Service life

Under normal service conditions, the product will have a life of at least equivalent to the structure in which it is incorporated, provided it is designed, installed and maintained in accordance with this Certificate and the Certificate holder's instructions.



PROCESS

Information provided by the Certificate holder was assessed for the following factors:

9 Design, installation, workmanship and maintenance

- 9.1 Design
- 9.1.1 General standards of good design practice are given in BS EN 1996-1-1: 2005, BS EN 1996-2: 2006 and BS EN 1996-3: 2006, and their UK National Annexes, and PD 6697: 2019.
- 9.1.2 The presence of the product can reduce the shear and tensile (and therefore bending) strengths of a wall at that point, and designs may need to take account of this. Allowable stresses on the DPC are detailed in the product literature and further guidelines are available from the Certificate holder.
- 9.1.3 Where there is doubt about the compatibility with materials in contact, the advice of the Certificate holder's Technical Department should be sought, but such advice is outside the scope of this Certificate.
- 9.2 Installation
- 9.2.1 Installation instructions provided by the Certificate holder were assessed and judged to be appropriate and adequate.
- 9.2.2 Installation must follow normal good practice for the detailing of damp-proof courses, as set out in PD 6697: 2019, and must be in accordance with the relevant clauses of BS 8000-3: 2020 and BS 8215: 1991, BRE Digest 380, and the Certificate holder's instructions.
- 9.2.3 The product must extend through the full thickness of the wall or wall-leaf, including pointing, applied rendering or other facing material.
- 9.2.4 The product must be laid on a wet, even bed of mortar, and perforations in adjacent courses of brickwork must be closed with mortar and project 5 mm beyond the finished face.
- 9.2.5 The product must always be sandwiched between wet mortar and not laid dry.
- 9.2.6 All lap joints in the product must have a minimum 100 mm overlap, be completely sealed with suitable tape and supported by a suitable joint system in accordance with the Certificate holder's instructions.
- 9.2.7 Preformed cavity tray units must be used at stop ends, and at all corners or changes in levels of cavity trays. Where the product is used as a cavity tray, all laps must be sealed.
- 9.2.8 In beam-and-block flooring, the product may be laid dry on a brick or block wall provided the following conditions are satisfied:
- 9.2.8.1 The minimum bearing of the beams recommended by the flooring system manufacturer is achieved. 9.2.8.2 The dead and applied loads upon the product via the beam do not exceed 2.5 N·mm⁻².
- 9.2.8.3 The surface of the wall onto which the product and beam are to be installed is clean, smooth and free from projections and perforations. Failure to comply with this requirement could lead to perforation of the product. If this requirement cannot be met, the product must be laid on an even bed of mortar.
- 9.2.8.4 Any loose aggregate is swept from the wall prior to installation of the product and from the product prior to installation of beam.



9.3 Workmanship

Practicability of installation was assessed by the BBA on the basis of the Certificate holder's information. To achieve the performance described in this Certificate, installation of the product must be carried out by a competent general builder, or a contractor, experienced with this type of product.

9.4 Maintenance and repair

- 9.4.1 As the product is confined within the wall and wall cavity, and has suitable durability, maintenance is not required.
- 9.4 2 Damaged areas of the product can be repaired prior to installation by cutting and/or replacing the damaged section, ensuring joints are made in accordance with section 9.2. Once covered, the product cannot be repaired.

10 Manufacture

- 10.1 The production processes for the product have been assessed, and provide assurance that the quality controls are satisfactory according to the following factors:
- 10.1.1 The manufacturer has provided documented information on the materials, processes, testing and control factors.
- 10.1.2 The quality control operated over batches of incoming materials has been assessed and deemed appropriate and adequate.
- 10.1.3 The quality control procedures and product testing to be undertaken have been assessed and deemed appropriate and adequate.
- 10.1.4 The process for management of non-conformities has been assessed and deemed appropriate and adequate.
- 10.1.5 An audit of each production location was undertaken, and it was confirmed that the production process was in accordance with the documented process, and that equipment has been properly tested and calibrated.
- †10.2 The BBA has undertaken to review the above measures on a regular basis through a surveillance process, to verify that the specifications and quality control operated by the manufacturer are being maintained.

11 Delivery and site handling

- 11.1 The Certificate holder stated that the product is delivered to site in rolls wrapped in pre-printed wrappers bearing the product name, roll dimensions and a roll manufacturing number. The rolls are packed on pallets with polythene wrapping.
- 11.2 Delivery and site handing must be performed in accordance with the Certificate holder's instructions and this Certificate, including:
- 11.2.1 Rolls must be stored on end and under cover. Contact with organic solvents must be avoided.
- 11.2.2 If stored at low temperatures, the DPC must be left in a warm place before use to improve handling.

ANNEX A - SUPPLEMENTARY INFORMATION †

Supporting information in this Annex is relevant to the product but has not formed part of the material assessed for the Certificate.

Construction (Design and Management) Regulations 2015 Construction (Design and Management) Regulations (Northern Ireland) 2016

Information in this Certificate may assist the client, designer (including Principal Designer) and contractor (including Principal Contractor) to address their obligations under these Regulations.

UKCA marking

The Certificate holder has taken the responsibility of UKCA marking the product in accordance with Designated Standard EN 14909 : 2012.

CE marking

The Certificate holder has taken the responsibility of CE marking the product in accordance with harmonised European

Standard EN 14909: 2012.

Additional information on installation

A.1 The product is handled and cut using the same techniques as those used for traditional flexible dampproof courses. It retains sufficient flexibility when used at the lowest temperature at which walls are normally built and does not become tacky in warm, ambient weather conditions.

A.2 Difficulties may occur when forming certain details, particularly when bending Plyload Extra through two angles at the same time. In such cases, care must be taken to achieve a satisfactory seal, and where necessary preformed cavity tray units should be used. Care should be taken at temperatures below 5°C to avoid the risk of condensation on jointed surfaces which may affect the efficiency of suitable self-adhesive tape.

A.3 When using Plyload Extra with boot lintels or similar constructions, it is recommended that the material is installed following the lintel profile, where appropriate.

A.4 As with other DPC materials, damage can occur during cleaning of mortar droppings from the DPC unless care is taken. The following recommendations minimise damage occurring:

- A.4.1 Cavity battens should be used to prevent excessive amounts of mortar droppings reaching the DPC.
- A.4.2 Mortar droppings should be removed before they have had time to harden.
- A.4.3 Implements such as steel rods should never be used for cleaning.
- A.4.4 Damp-proof courses should be examined for damage as work proceeds.



Bibliography

BRE Digest 380 Damp-proof courses

BS 8000-3 : 2020 Workmanship on building sites — Code of practice for masonry

BS 8215: 1991 Code of practice for design and installation of damp-proof courses in masonry construction

BS DD 86-1: 1983 Methods of test for flexural bond strength and short-term shear strength

BS EN 495-5 : 2001 Flexible sheets for waterproofing — Determination of foldability at low temperature — Plastic and rubber sheets for roof waterproofing

BS EN 1928 : 2000 Flexible sheets for waterproofing — Bitumen, plastic and rubber sheets for roof waterproofing — Determination of watertightness

BS EN 1931 : 2000 Flexible sheets for waterproofing — Bitumen, plastic and rubber sheets for roof waterproofing — Determination of water vapour transmission properties

BS EN 1996-1-1 : 2005 + A1 : 2012 Eurocode 6 — Design of masonry structures — General rules for reinforced and unreinforced masonry structures

NA to BS EN 1996-1-1 : 2005 + A1 : 2012 UK National Annex to Eurocode 6 — Design of masonry structures — General rules for reinforced and unreinforced masonry structures

BS EN 1996-2 : 2006 Eurocode 6 — Design of masonry structures — Design considerations, selection of materials and execution of masonry

NA to BS EN 1996-2 : 2006 UK National Annex to Eurocode 6 — Design of masonry structures — Design considerations, selection of materials and execution of masonry

BS EN 1996-3 : 2006 Eurocode 6 — Design of masonry structures : Simplified calculation methods for unreinforced masonry structures

NA + A1 : 2014 to BS EN 1996-3 : 2006 UK National Annex to Eurocode 6 - Design of masonry structures : Simplified calculation methods for unreinforced masonry structures

BS EN 12310-1 : 2000 Flexible sheets for waterproofing — Determination of resistance to tearing (nail shank) — Bitumen sheets for roof waterproofing

BS EN 12317-2 : 2000 Flexible sheets for waterproofing — Determination of shear resistance of joints — Plastic and rubber sheets for roof waterproofing

BS EN 12691 : 2006 Flexible sheets for waterproofing — Bitumen, plastic and rubber sheets for roof waterproofing — Determination of resistance to impact

BS EN 12730 : 2001 Flexible sheets for waterproofing — Bitumen, plastic and rubber sheets for roof waterproofing — Determination of resistance to static loading

BS EN 13501-1 : 2018 Fire classification of construction products and building elements — Classification using data from reaction to fire tests

EN 14909 : 2012 Flexible sheets for waterproofing — Plastic and rubber damp-proof courses — Definitions and characteristics

PD 6697 : 2019 Recommendations for the design of masonry structures to BS EN 1996-1-1 and BS EN 1996-2



Conditions of Certificate

Conditions

1 This Certificate:

- relates only to the product that is named and described on the front page
- is issued only to the company, firm, organisation or person named on the front page no other company, firm, organisation or person may hold or claim that this Certificate has been issued to them
- · is valid only within the UK
- has to be read, considered and used as a whole document it may be misleading and will be incomplete to be selective
- is copyright of the BBA
- · is subject to English Law.

2 Publications, documents, specifications, legislation, regulations, standards and the like referenced in this Certificate are those that were current and/or deemed relevant by the BBA at the date of issue or reissue of this Certificate.

3 This Certificate will be displayed on the BBA website, and the Certificate Holder is entitled to use the Certificate and Certificate logo, provided that the product and its manufacture and/or fabrication, including all related and relevant parts and processes thereof:

- are maintained at or above the levels which have been assessed and found to be satisfactory by the BBA
- continue to be checked as and when deemed appropriate by the BBA under arrangements that it will determine
- are reviewed by the BBA as and when it considers appropriate.

4 The BBA has used due skill, care and diligence in preparing this Certificate, but no warranty is provided.

5 In issuing this Certificate the BBA is not responsible and is excluded from any liability to any company, firm, organisation or person, for any matters arising directly or indirectly from:

- · the presence or absence of any patent, intellectual property or similar rights subsisting in the product or any other product
- the right of the Certificate holder to manufacture, supply, install, maintain or market the product
- · actual installations of the product, including their nature, design, methods, performance, workmanship and maintenance
- any works and constructions in which the product is installed, including their nature, design, methods, performance, workmanship and maintenance
- · any loss or damage, including personal injury, howsoever caused by the product, including its manufacture, supply, installation, use, maintenance and removal
- any claims by the manufacturer relating to UKCA marking and CE marking.

6 Any information relating to the manufacture, supply, installation, use, maintenance and removal of this product which is contained or referred to in this Certificate is the minimum required to be met when the product is manufactured, supplied, installed, used, maintained and removed. It does not purport in any way to restate the requirements of the Health and Safety at Work etc. Act 1974, or of any other statutory, common law or other duty which may exist at the date of issue or reissue of this Certificate; nor is conformity with such information to be taken as satisfying the requirements of the 1974 Act or of any statutory, common law or other duty of care.

©2023

British Board of Agrément

1st Floor, Building 3, Hatters Lane, Croxley Park, Watford Herts WD18 8YG

tel: 01923 665300 clientservices@bbacerts.co.uk www.bbacerts.co.uk

