

Technical Properties: PLYFORM ABS GP				
Construction:		Multi-layer or mono-layer general purpose grade ABS		
Edition / Date:		5 / 08-07-2024		
Characteristics		Value*	Unit*	Test method*
PHYSICAL PROPERTIES				
Density	23°C	1.06	g/cm ³	ASTM D 792
MECHANICAL PROPERTIES				
Tensile E-Modulus	23°C	1999.5	MPa	ASTM D 638
Yield stress	23°C	35.8	MPa	ASTM D 638
Elongation at break	23°C	28	%	ISO 527
IZOD notched impact strength	23°C	261.5	J/m	ASTM D 256
	-30°C	101.4	J/m	ASTM D 256
THERMAL PROPERTIES				
Vicat B	50°C/h 50N	97	°C	ISO 306
HDT-A	1.82 MPa	80	°C	ASTM D 648
BURNING BEHAVIOUR				
Flammability classification		HB		UL 94
MISCELLANEOUS PROPETIS				
Moulding shrinkage		0.5 – 0.7	%	General test method
Thermoforming temperature range		160 to 210	°C	General test method

*tested on raw material (natural colour)

This technical data has been developed by Plysolene Ltd in good faith. This data is non-binding and does not represent a material specification or assurance of specific properties. We reserve the right to change or update these specifications at any time.

Further processing and use of the product can have various impacts on the product. Therefore, Plysolene Ltd does not guarantee or warrant for the fitness or suitability of products for any purpose intended by the purchaser or any third person and shall have no liability whatsoever in this respect. The purchaser has the obligation to test the product and determine themselves if the product is fit for the intended use.